



Alpha Stone Talc Powder is known by its highest purity and whiteness with low iron, silica and magnesium percentages

Technical Data Sheet


Typical Chemical Properties %	
SiO ₂	60-62
TiO ₂	<0.01
Al ₂ O ₃	0.3-0.5
Fe ₂ O ₃	0.1-0.2
MnO	0.01
MgO	31-33
CaO	0.14-0.3
Na ₂ O	<0.01
K ₂ O	<0.01
P ₂ O ₅	0.01
L.O.I (ASTM D7348)	13±1

Free of Asbestos

Typical Physical Properties	
Bulk Density (gm/ml)	0.28
Tapped Density (gm/ml)	0.78
Oil Absorption ±1	53gm per 100gm powder
Density (ISO 787/10) g/ml	2.7
Hardness (Mohs)	1
PH value (787/9)	9
Moisture	0.2%Max

PSD	(Sedigraph III)	(MALVERN)
D98 (μ)	11.5±0.5	24±2
D97 (μ)	10.5±0.5	22±2
D50 (μ)	2.8± 0.2	7.5±0.5
Color (ELREPHO)		
(RY)	86±1	
(L*)	94±1	
(a*)	-0.03	
(b*)	1.66	

Particle size distribution



Packing

25 Kg	Plastic/Paper Bags
750 Kg	Jumbo Bags

Last Update 7-5-2026

Factory: Egypt- El Minya- industrial zone -El-Motahra

HQ Office :66 Mohamed Farid Abo Haded St., Nasr city , Cairo

Tel: (+2) 0862290004 – 0869202737 - 022876613

Fax: (+2) 0862290005 - 022876613

Mobile : (+2) 01001050113 -01227348893- 01003405080



Website: www.alphastone-eg.com

Email: alphastone.factory@yahoo.com

المصنع : مصر- محافظة المنيا -المنطقة الصناعية -المطاهرة

المقر الإداري: 66 شارع محمد فريد أبو حديد - القاهرة - مدينة نصر

ت: (+2) 0862290004 – 0869202737 – 022876613

فكس: (+2) 0862290005 - 022876613

موبايل: (+2) 01001050113 -01227348893- 01003405080